

TECHNICAL DATA SHEET

615 S 4th Street, Elkhart, IN 46516-2717 Ph: 833-BIG-DOGG (833-244-3644) Page 1 of 1 December 2018

BD5405 Epoxy Adhesive

1. DESCRIPTION:

BD5405 is a two-part, room temperature cure, epoxy adhesive with good chemical resistance. It has a low viscosity for good substrate penetration and adhesion. It is especially formulated for a 1:1 mix ratio for use in side by side cartridges, or to be used by hand mixing, or use with Meter Mix Equipment.

2. CHARACTERISTICS:

Room Temperature Cure Properties

Work Time: 3 to 5 minutes (at 75°F/24°C) Fixture Time: 20 to 30 minutes (at 75°F/24°C)

Full Cure: 1 hour movement;

24 hours for full properties
Operating Temp.

40°F(40°C) to 266°F (130°C)
Mixed Density:
9.5 lbs/gal (1.15 g/cc)
Flash Point:
Greater than 200°C (392°F)

Viscosity: Greater than 200°C (392°F)

Resin (Part A) 12,000 CPS

Hard (Part B) 13,000 CPS

Color: Resin (Part A) Clear

Activator (Part A) Clear
Mixed: Clear

Mix Ratio: 1 Part A to 1 Part B (1:1)

Hardness: 80 Shore D

Tensile Strength: > 2,500 PSI (AL to AL)

Tensile Strength 7,100 PSI Elongation: 5 %

Impact Resistance:> 150 inch/lbWater Absorption:< 1% (24 hours)</td>Shelf Life:24 MonthsVOC Content:0% by weight

3. Handling and Storage:

- A. Bring both components to room temperature prior to mixing. Mix 1 part A to 1 part B by volume or weight thoroughly for 30 seconds minutes.
- B. Dispense mixed material over properly positioned devices to be glued together. Do not pour more than 1/2" thick as the product may exotherm too high and may boil. As this is a very quick adhesive, you must work quickly to bond the pieces together.
- Parts may be shipped within 24 hours but parts can be moved in 1 hour.

4. ADDITIONAL INFORMATION

NOTE: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. The Company shall not be liable for any injury, loss, or damage in the use or handling of its chemical products since conditions and use are beyond our control. In every case, we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitability for their particular purpose under their own operating conditions. Statements concerning possible use of our products are not intended as recommendations to use our products in the infringement of any patent, or for any particular purpose or application. These products are intended for industrial use only.