

BD8710 Low Odor Structural Methacrylate Adhesive

1. DESCRIPTION

BD8710 is a two-part methacrylate, structural bonding adhesive designed for the structural bonding of various substrates, including fiberglass, steel, aluminum, and various thermoplastics assemblies. Combined at a ratio of 10:1, BD8710 has a working time of 8 to 12 minutes and achieves a structural strength of 1000 psi at 20 minutes at room temperature curing. BD8710 provides high bond strength to the above reference surfaces with generally no preparation effort.

Company Identification: Big Dog Adhesives LLC.

435 Harrison Street
Elkhart, IN 46516-2717
Toll-free: 833-BIG-DOGG (833-244-3644)
Fax: 833-BIG-DOGZ (833-244-3649)
Website: www.bigdogadhesives.com lou@bigdogadhesives.com

2. CHARACTERISTICS:

Room Temperature Cure

- Working Time
- Fixture Time
- Can be Moved In
- Gap Filling

Properties

8 to 12 minutes (at 75°F/ 24°C)
15 to 20 minutes (at 75°F/ 24°C)
20minutes
0.01 – 0.125 inches

3. CHEMICAL RESISTANCE:

Excellent Resistance to:

- Hydrocarbons
- Weak Acids and Bases

Susceptible to:

Polar Solvents
Strong Acids and Bases

4. PHYSICAL PROPERTIES:

Uncured:

- Viscosity(cps)
- Color

Resin

60,000 – 100,000
Black

Activator

10,000 – 40,000
Grey

5. MECHANICAL PROPERTIES:

Tensile Strength (ASTM D1002)

- Strength, psi
- Strength, psi

Substrate

Steel
Aluminum

Results

1500 – 2000
1500 – 2,000

Failure Type

Cohesive
Cohesive

6. HANDLING AND APPLICATION:

Contents include Methacrylate ester and acids. Keep containers closed after use. Wear gloves and safety glasses to avoid skin and eye contact. Wash with soap and water after skin contact. In case of eye contact, flush with water for 15 minutes and get medical attention. Harmful if swallowed. Keep out of the reach of children. Keep away from heat, sparks, and open flames. Do not smoke cigarettes or anything else while handling or near the product. Refer to the BD8710 Safety Data Sheet for more complete safety instruction. To assure maximum bond strength, surfaces must be mated together within the specified working time, and all clamps affixed within that time. Use sufficient material to ensure that the joint is completely filled when parts are mated and clamped. Avoid over clamping parts, which may cause a dry joint or a joint starved of adhesive. All adhesive

application, part positioning, fixturing, and clamping should occur before the working time of the adhesive has expired. After the indicated working time, parts must remain undisturbed until the fixture time is completed. Components bonded, adhesive, and shop temperature can have a significant effect on the work and fixture time of the adhesive. Application of BD8710 adhesive at temperatures between 65°F and 85°F (18°C and 30°C) will ensure proper cure. Temperatures below 65°F (18°C) will slow cure and fixture speed. BD8710 adhesives will still react, but will take longer. Temperatures above 85°F (18°C and 30°C) will increase cure and fixture speeds, and there's a risk that the adhesive will be hardened or too thick to bond materials. The viscosities of BD8710 adhesives are affected by temperature.

NOTE: Because of the curing features of BD8710 adhesives, large amounts of heat are generated when large masses of material are mixed at one time. The heat generated by the exotherm resulting from mixing large amounts of adhesive can result in a boiling of the monomer in the adhesive (methyl methacrylate), resulting in the release of trapped air, steam and volatile gasses. To prevent this, use only enough material as needed for use within the working time for the product, and confine the gap or spread out the material to no more than .50 inches.

7. HANDLING AND STORAGE

The shelf life of BD8710 is twelve (12) months from the date of manufacture based upon continuous storage at room temperature (77°F or 25°C). Storage of BD8710 adhesives in refrigerated compartments will extend the shelf life even more. Do not store BD8710 adhesive or any other adhesives in a refrigerator which has food or lunch products in them. Be sure to bring BD8710 adhesives to room temperature for 24 hours before use, otherwise longer cure and fixture times may be expected. Long-term storage at temperatures above room temperature will shorten the shelf life of BD8710 adhesives considerably. Storage at temperatures above 100°F or 38°C could shorten the shelf life to less than one month. BD8710 adhesives contain no water, so freezing of the adhesive for short periods is permissible, but is not encouraged.

8. ADDITIONAL INFORMATION

NOTE: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. The Company shall not be liable for any injury, loss, or damage in the use or handling of its chemical products since conditions and use are beyond our control. In every case, we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitability for their particular purpose under their own operating conditions. Statements concerning possible use of our products are not intended as recommendations to use our products in the infringement of any patent, or for any particular purpose or application. These products are intended for industrial use only.