

TECHNICAL DATA SHEET

615 S 4th Street, Elkhart, IN 46516-2717 Ph: 833-BIG-DOGG (833-244-3644) Page 1 of 1 September 2024

BDRP 2400 Cyanoacrylate Adhesive

1. DESCRIPTION:

BDRP 2400 is a high viscosity, rapid curing, cyanoacrylate adhesive. It is designed to bond a wide variety of similar and dissimilar materials. The handling strength in most applications is in the 15 to 20 seconds time period.

2. CHARACTERISTICS:

Color:ClearViscosity:2400 cpsSpecific Color:1.07Base:Ethyl

3. Performance Properties:

Substrate	Fixture Time	Bond Strength	
Steel	<18 seconds	>2,200 PSI	
Aluminum	<15 seconds	>1,800 PSI	
Neoprene	< 4 seconds	> 800 PSI	
ABS	< 8 seconds	> 900 PSI	
PVC	< 5 seconds	> 900 PSI	
Lexan	< 25 seconds	> 900 PSI	
Phenolic	< 10 seconds	> 900 PSI	
Note: ISO4587 is the method used			

Note: ISO4587 is the method used.

4. Electrical Properties:

Dielectric Constant ASTM D150 Dissipation Factor 1 kHz 2.0 to 3.50/< .02

Volume Resistivity ASTM D257: 2 to 10 x 10¹⁵

5. Factors Affecting Cure Speed:

GAP: Thin bond lines result in faster cure speed. The larger bond gaps will lengthen cure speed. **HUMIDITY:** Cyanoacrylates cure as a function of water content. Higher humidity will cure products faster. Fixture times are normally measured at 50% relative humidity (RH).

6. Chemical/Solvent Resistance:

Percent of Strength retained after aging for 500 hours		
Gasoline at 75F	100%	
Isopropanol (IPA) at 75F	100%	
Ethanol (Denatured Alcohol) at 75F	100%	
Freon TA at 75F	100%	
Motor Oil at 105F	100%	
Lexan (polycarbonate) at 105F & 95% RH	100%	

7. What Cyanoacrylates Bond:

ABS NBR Acrylic Neoprene Aluminum Nitrile Rubber Bakelite Nylon Phenolic Brass Chloroprene Polycarbonate Chrome Polyester Polystyrene Copper Porcelain **EPDM PVC** Fiberglass Latex SBR Leather Skin Natural Rubber Steel Wood Valox

8. Directions for use and Storage:

For optimum results, parts should be clean and free from any oils, contamination or loose surfaces (rust). If parts do not mate flush or closely together, you will need to use a product that has higher viscosity to compensate for the gap. Any excess adhesive can be removed with Debonder. Store in unopened containers, out of the direct sunlight, in a dry location, at room temperature (75F). Refrigeration can extend shelf life.

9. ADDITIONAL INFORMATION

NOTE: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. The Company shall not be liable for any injury, loss, or damage in the use or handling of its chemical products since conditions and use are beyond our control. In every case, we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitability for their particular purpose under their own operating conditions. Statements concerning possible use of our products are not intended as recommendations to use our products in the infringement of any patent, or for any particular purpose or application. These products are intended for industrial use only.